


VAUTID 70

Tubular wire and welding rod

Hardfacing material for high impact, shock and abrasion

VAUTID®

VAUTID Material characteristics



Specification	Tubular wire electrode DIN EN 14700 T Fe6 gp Welding rod DIN EN 14700 E Fe6 gp
Material type Alloy components	Medium-alloyed, martensitic Cr–Mo–C hard alloy on iron base with Ti special carbides C – Cr – Mo – Ti – Fe
Weld deposit characteristics	VAUTID 70 produces a hardened welding deposit resistant to abrasion and impact. The weld deposit is magnetic and cannot be machined in welding conditions. Machining of the annealed material is possible. Crack-free hardfacings up to 10 mm thickness are possible
Weld deposit properties	Hardness 1st layer on S235JR: approx. 42 – 48 HRC* Hardness (acc. DIN 32525-4): approx. 50 – 56 HRC*
Recommended applications	Perfectly suited for parts subjected to combined shock and abrasive stresses as well as metal-to-metal wear: percussion borers, pick hammers, dredger teeth, crusher rolls and guide rails. Also suited for the hardfacing of tools including those for hot forming. Resistant to heat wear up to approx. 670° C
Standard sizes	Tubular wires: Diameter 1,2 / 1,6 / 2,0 / 2,4 / 2,8 / 3,2 mm Packing: Mandrels 15 kg, Reels 25 kg, Drums 250 kg Welding rods: Diameter 3,25 / 4,0 / 5,0 / 6,0 mm Packing: 5 kg packages

* subject to common industrial fluctuations

Welding instructions for tubular wires:

VAUTID 70 tubular wires are slagging and are welded without inert gas on the +pole. Both the weave bead and stinger bead techniques can be used. Weaving and preheating prevent cracking. The thickness of the surfacing should be limited to 10 mm.

Diameter (mm)	Current (A)	Voltage (V)	Stick out (mm)
1,2	100 – 220	18 – 22	20 – 30
1,6	160 – 250	22 – 24	20 – 35
2,0	180 – 300	22 – 24	25 – 40
2,4	240 – 380	26 – 28	30 – 45
2,8	300 – 470	26 – 28	30 – 50
3,2	290 – 470	28 – 30	30 – 55

Welding instructions for welding rods:

VAUTID 70 welding rods are slagging and can be welded with d.c. on the +pole but also with a.c. The thickness of the surfacing should be limited to 10 mm.

It is not necessary to re-dry the electrodes prior to welding.

Diameter (mm)	Current (A)
3,25	100-120
4,0	120-160
5,0	170-210
6,0	230-250

Welding positions (EN ISO 6947): PA, PB

This data sheet corresponds to the present state of production (October 2016) and can be changed anytime.

VAUTID GROUP
Brunnwiesenstr. 5
73760 Ostfildern

Phone: + 49 711 / 44 04-0
Fax: + 49 711 / 44 20 39

E-Mail: vautid@vautid.de
Web: www.vautid.com